

**Strassburger Filter
GmbH & Co. KG**

S P E C I F I C T E S T R E P O R T

(according to DIN 50049 - 2.3 / EN 10204 - 2.3)

SF – SS 0 (400 x 400 mm)

Batch No.: 221602601

Production date: 18-02-26 (yy.mm.dd)

We accept sole responsibility in stating that the product conforms to the presently valid and agreed specifications.

Depth filter sheets are products for solid/liquid separation in sterilizing or microorganism-reducing filtration, polishing or coarse filtration.

		Average batch values
Water flow rate Δp 100 kPa	L/m ² /min	97
Weight per unit area	g/m ²	1298
Thickness	mm	3,8
Ash content	%	48
Extractable ions	mg/m ²	Approx. values
Soluble in: acetic acid (5%) e.g.	Ca	1500
	Fe	10
	Al	100

The tests are carried out as per the methods of the European Association of Depth Filtration e.V. or in accordance with company-specific test procedures.

Heavy metals as per recommendation XXXVI/1 within the Lebensmittel- und Futtermittelgesetzbuch - LFGB - (German Foodstuffs and Animal Feed Code) (ppm) **< 50**

Bacteria retention capability with *Brevundimonas diminuta*:
LRV (Log Reduction Value) **6,5**
(according to the method of the European Association of Depth Filtration e.V)

The product conforms to the recommendation XXXVI/1 and meets the requirements of the Lebensmittel- und Futtermittelgesetzbuch - LFGB - (German Foodstuffs and Animal Feed Code) especially §§ 30 and 31. It may without any reservation be used for cold filtration of foodstuffs.

<u>Main components:</u>	cellulose	<u>Components < 3 %:</u>	resins corresponding to the recommendation XXXVI resp.
	natural diatomaceous earth		21 CFR
	perlite		polyolefine fibres

Safe filtration requires that all process parameters relevant to a special application have been validated. The above statements do not rescind from the obligation to perform an incoming goods control. All above information are based on our present state of knowledge and do not claim to be complete. The use resp. handling of our products is in the buyer's responsibility also with regard to possible protective rights of third parties.

The depth filter sheets should be used within 3 years of production.

Westhofen, 12-04-2018

.....
Julia Schnitzler (General Manager)

This document has been made by computer and is valid without a signature